

# CODE 110M : Gravillon 11/22

**Producteur :** GKM - Carrières de Mouen  
**Petrographie :** Grès feldspathique  
**Elaboration :** Tertiaire

## Partie contractuelle

Valeurs spécifiées sur lesquelles le producteur s'engage

Classe granulaire

Norme

CODE

11.2 22.4

Norme NF P 18-545 Article 10

Gr A

	d/2	d	D	1.4D	2D	f	FI	AS	LA	MBF	S	WA24
	5.6	11.2	22.4	31.5	45							
Incertitude U	1	5	5	1	0	0.3	4	0.15	3	2	0.1	0.5
V.S.S.+U	6.0	20.0	100.0	100.0	100.0	1.80	24.00	0.350	28	12.00	0.500	3.0
V.S.S.	5.0	15.0	99.0	100.0	100.0	1.50	20.00	0.200	25	10.00	0.400	2.5
V.S.I.	0.0	0.0	84.0	98.0	100.0	0.00						
V.S.I.-U	0.0	0.0	79.0	97.0	100.0	0.00						
Ecart-type max	1.52	4.55	4.55									

## Partie informative

Résultats de production

	du 22/01/19 au 25/06/19						du 17/05/19 au 17/05/19					
	5.6	11.2	22.4	31.5	45	f	FI	AS	LA	MBF	S	WA24
Maximum	1.9	6.3	99.0	100.0	100.0	0.93	8.70					
Xf+1.25xEcart-types	1.2	3.2	99.0	100.0	100.0	0.74						
Moyenne Xf	0.7	1.3	97.9	100.0	100.0	0.45	7.49	0.018	15	3.33	0.019	0.8
Xf-1.25xEcart-types	0.1	0.0	96.9	100.0	100.0	0.16						
Minimum	0.0	0.4	96.0	100.0	100.0	0.05	6.03					
Ecart-type	0.48	1.51	0.81	0.00	0.00	0.233	1.019					
Nombre de résultats	16	16	16	17	17	16	7	1	1	1	1	1

