

CODE 110M : Gravillon 11/22 MOUEN

Producteur : GKM - Carrières de Mouen
Petrographie : Grès feldspathique
Elaboration : Tertiaire

Partie contractuelle
Valeurs spécifiées sur lesquelles le producteur s'engage

Classe granulaire	Norme					CODE								
	11.2	22.4	Norme NF P 18-545 Article 10					Gr A						
	d/2	d	D	1.4D	2D	f	FI	AS	C	LA	MBF	S	WA24	
Incertitude U	1	5	5	1	0	0.3	4	0.15	0.003	3	2	0.1	0.5	
V.S.S.+U	6.0	20.0	100.0	100.0	100.0	4.30	24.00	0.350	0.013	28	12.00	0.500	3.0	
V.S.S.	5.0	15.0	99.0	100.0	100.0	4.00	20.00	0.200	0.010	25	10.00	0.400	2.5	
V.S.I.	0.0	0.0	84.0	98.0	100.0	0.00								
V.S.I.-U	0.0	0.0	79.0	97.0	100.0	0.00								
Ecart-type max	1.52	4.55	4.55											

Partie informative
Résultats de production

	du 10/06/20 au 09/12/20							au 31/07/20						
	5.6	11.2	22.4	31.5	45	f	FI	AS	C	LA	MBF	S	WA24	
Maximum	1.7	4.6	99.7	100.0	100.0	0.96	9.12							
Xf+1.25xEcart-types	1.4	2.9	99.7	100.0	100.0	0.84								
Moyenne Xf	0.9	1.7	98.2	100.0	100.0	0.58	8.35	0.023	0.001	14	3.33	0.007	0.6	
Xf-1.25xEcart-types	0.3	0.5	96.8	100.0	100.0	0.31								
Minimum	0.1	0.6	94.1	100.0	100.0	0.12	7.45							
Ecart-type	0.42	0.99	1.15	0.00	0.00	0.213	0.548							
Nombre de résultats	23	23	23	24	24	23	6	1	1	1	1	1	1	

