

CODE 115M : Gravillon 10/14 MOUEN

Producteur : GKM - Carrières de Mouen

Petrographie : Grés

Elaboration : Concassé tertiaire

Partie contractuelle

Valeurs spécifiées sur lesquelles le producteur s'engage

Classe granulaire

Norme

CODE

10 14

Norme NF P 18-545 Article 10

Gr A

	d/2	d	D	1.4D	2D	f	FI	LA	MBF	AS	S	WA24
	5	10	14	20	28							
Incertitude U	1	5	5	1	0	0.6	4	3	2	0.15	0.1	0.5
V.S.S.+U	6.0	25.0	100.0	100.0	100.0	4.60	24.00	28	12.00	0.350	0.500	3.0
V.S.S.	5.0	20.0	95.0	100.0	100.0	4.00	20.00	25	10.00	0.200	0.400	2.5
V.S.I.	0.0	5.0	80.0	98.0	100.0							
V.S.I.-U	0.0	0.0	75.0	97.0	100.0							

Partie informative

Résultats de production

	du 04/06/18 au 05/11/18							du 16/07/18 au 16/07/19				
	5	10	14	20	28	f	FI	LA	MBF	AS	S	WA24
Maximum	2.5	18.1	94.7	100.0	100.0	1.33	9.12					
Xf+1.25xEcart-types	2.0	14.7	93.8	100.0	100.0	0.87						
Moyenne Xf	1.1	11.7	90.3	100.0	100.0	0.53	7.97	14	3.33	0.018	0.019	0.5
Xf-1.25xEcart-types	0.1	8.7	86.7	100.0	100.0	0.19						
Minimum	0.3	8.4	85.4	100.0	100.0	0.19	6.38					
Ecart-type	0.75	2.38	2.85	0.00	0.00	0.272	1.035					
Nombre de résultats	17	17	17	17	17	17	5	1	1	1	1	1

