

# CODE 112M : Gravillon 5/22 MOUEN

**Producteur :** GKM - Carrières de Mouen  
**Petrographie :** Grès feldspathique  
**Elaboration :** Tertiaire

## Partie contractuelle

Valeurs spécifiées sur lesquelles le producteur s'engage

Classe granulaire

Norme

CODE

5.6 22.4

Norme NF P 18-545 Article 10

Gr A

	d/2	d	D/2	D	1.4D	2D	f	FI	AS	LA	MBF	S	WA24
	2.8	5.6	11.2	22.4	31.5	45							
Incertitude U	1	5	6	2	1	0	0.3	4	0.15	3	2	0.1	0.5
V.S.S.+U	6.0	20.0	66.0	100.0	100.0	100.0	4.30	24.00	0.350	28	12.00	0.500	3.0
V.S.S.	5.0	15.0	60.0	99.0	100.0	100.0	4.00	20.00	0.200	25	10.00	0.400	2.5
V.S.I.	0.0	0.0	25.0	84.0	98.0	100.0	0.00						
V.S.I.-U	0.0	0.0	19.0	82.0	97.0	100.0	0.00						
Ecart-type max	1.52	4.55	10.61	4.55									

## Partie informative

Résultats de production

	du 17/01/19 au 25/06/19							du 17/05/19 au 17/05/19					
	2.8	5.6	11.2	22.4	31.5	45	f	FI	AS	LA	MBF	S	WA24
Maximum	2.7	5.0	45.9	98.9	100.0	100.0	1.76	9.18					
Xf+1.25xEcart-types	1.8	3.5	41.2	99.0	100.0	100.0	1.23						
Moyenne Xf	0.9	2.1	33.2	98.4	100.0	100.0	0.64	8.72	0.018	15	3.33	0.019	0.8
Xf-1.25xEcart-types	0.1	0.7	25.1	97.8	100.0	100.0	0.06						
Minimum	0.1	0.6	25.2	97.4	100.0	100.0	0.03	7.94					
Ecart-type	0.69	1.15	6.47	0.49	0.00	0.00	0.468	0.425					
Nombre de résultats	15	15	15	15	15	15	15	6	1	1	1	1	1

