

CODE 112M : Gravillon 5.6/22.4 MOUEN

Producteur : GKM - Carrières de Mouen
Petrographie : Grès feldspathique
Elaboration : Tertiaire

Partie contractuelle

Valeurs spécifiées sur lesquelles le producteur s'engage

Classe granulaire

Norme

CODE

5.6 22.4

Norme NF P 18-545 Article 10

Gr A

	d/2	d	D/2	D	1.4D	2D	f	FI	AS	C	LA	MBF	S	WA24
	2.8	5.6	11.2	22.4	31.5	45								
Incertitude U	1	5	6	2	1	0	0.3	4	0.15	0.003	3	2	0.1	0.5
V.S.S.+U	6.0	20.0	66.0	100.0	100.0	100.0	4.30	24.00	0.350	0.013	28	12.00	0.500	3.0
V.S.S.	5.0	15.0	60.0	99.0	100.0	100.0	4.00	20.00	0.200	0.010	25	10.00	0.400	2.5
V.S.I.	0.0	0.0	25.0	84.0	98.0	100.0	0.00							
V.S.I.-U	0.0	0.0	19.0	82.0	97.0	100.0	0.00							
Ecart-type max	1.52	4.55	10.61	4.55										

Partie informative

Résultats de production

	du 10/06/20 au 09/12/20								au 31/07/20					
	2.8	5.6	11.2	22.4	31.5	45	f	FI	AS	C	LA	MBF	S	WA24
Maximum	1.7	3.5	41.3	99.7	100.0	100.0	1.18	9.93						
Xf+1.25xEcart-types	1.3	3.0	36.7	99.9	100.0	100.0	1.00							
Moyenne Xf	0.8	2.2	32.2	98.6	100.0	100.0	0.64	8.54	0.023	0.001	14	3.33	0.007	0.6
Xf-1.25xEcart-types	0.3	1.3	27.6	97.2	100.0	100.0	0.28							
Minimum	0.2	1.1	25.0	95.4	100.0	100.0	0.11	7.56						
Ecart-type	0.38	0.68	3.62	1.08	0.00	0.00	0.289	0.977						
Nombre de résultats	25	25	25	25	25	25	25	6	1	1	1	1	1	1

