

CODE 112E : Gravillon 5.6/22.4 Etavaux

Producteur : GKM - Carrières d' Etavaux

Petrographie : Gréso-Schisteux

Elaboration : Concassé Lavé

Partie contractuelle

Valeurs spécifiées sur lesquelles le producteur s'engage

Classe granulaire

Norme

CODE

5.6 22.4

Norme NF P 18-545 Article 10

B

	d/2	d	D/2	D	1.4D	2D	AS	f	FI	LA	MBF	S	WA24
	2.8	5.6	11.2	22.4	31.5	45							
Incertitude U	1	5	6	5	1	0	0.15	4	4	3	2	0.1	0.5
V.S.S.+U	6.0	20.0	66.0	100.0	100.0	100.0	0.350	8.00	39.00	28	12.00	0.500	3.0
V.S.S.	5.0	15.0	60.0	99.0	100.0	100.0	0.200	4.00	35.00	25	10.00	0.400	2.5
V.S.I.	0.0	0.0	25.0	84.0	98.0	100.0							
V.S.I.-U	0.0	0.0	19.0	79.0	97.0	100.0							
Ecart-type max	1.52	4.55	10.61										

Partie informative

Résultats de production

du 01/07/20 au 17/12/2020

	2.8	5.6	11.2	22.4	31.5	45	AS	f	FI	LA	MBF	S	WA24
Maximum	2.4	5.5	35.0	99.0	100.0	100.0		1.07	24.05				
Xf+1.25xEcart-types	2.2	4.5	32.1	99.0	100.0	100.0		0.95					
Moyenne Xf	1.4	2.7	28.5	96.7	99.9	100.0	0.028	0.60	21.23	16	3.33	0.019	0.5
Xf-1.25xEcart-types	0.6	1.0	25.0	94.5	99.6	100.0		0.24					
Minimum	0.3	0.8	24.9	93.1	99.0	100.0		0.12	19.56				
Ecart-type	0.65	1.42	2.84	1.79	0.24	0.00		0.281	1.612				
Nombre de résultats	18	18	18	18	18	18	1	18	7	1	1	1	1

