

# CODE 111E : Gravillon 5.6/11.2 Etavaux

**Producteur :** GKM - Carrières d' Etavaux

**Petrographie :** Grés-Schisteux

**Elaboration :** Tertiaire

## Partie contractuelle

Valeurs spécifiées sur lesquelles le producteur s'engage

**Classe granulaire**

**Norme**

**CODE**

5.6      11.2

Norme NF P 18-545 Article 10

A

	d/2	d	D	1.4D	2D	f	FI	AS	C	LA	MBF	S	WA24
	2.8	5.6	11.2	16	22.4								
Incertitude U	1	5	5	1	0	0.3	4	0.15	0.003	3	2	0.1	0.5
V.S.S.+U	6.0	21.0	100.0	100.0	100.0	1.80	24.00	0.350	0.013	28	12.00	0.500	3.0
V.S.S.	5.0	16.0	98.0	100.0	100.0	1.50	20.00	0.200	0.010	25	10.00	0.400	2.5
V.S.I.	0.0	1.0	83.0	98.0	100.0	0.00							
V.S.I.-U	0.0	0.0	78.0	97.0	100.0	0.00							
Ecart-type max	1.52	4.55	4.55										

## Partie informative

Résultats de production

	du 01/06/20 au 07/12/20							au 31/07/20					
	2.8	5.6	11.2	16	22.4	f	FI	AS	C	LA	MBF	S	WA24
Maximum	1.6	9.4	93.9	100.0	100.0	0.94	17.89						
Xf+1.25xEcart-types	1.1	7.7	91.9	100.0	100.0	0.44							
Moyenne Xf	0.7	5.2	88.0	100.0	100.0	0.24	14.33	0.028	0.001	16	3.66	0.019	0.5
Xf-1.25xEcart-types	0.3	2.7	84.1	99.9	100.0	0.04							
Minimum	0.2	2.0	80.8	99.7	100.0	0.07	8.82						
Ecart-type	0.31	1.99	3.12	0.06	0.00	0.162	2.869						
Nombre de résultats	33	33	33	33	33	33	11	1	1	1	1	1	1

