

# CODE 105M : Gravillon 5.6/11.2 MOUEN

**Producteur :** GKM - Carrières de Mouen  
**Petrographie :** Grès feldspathique  
**Elaboration :** Tertiaire

## Partie contractuelle

Valeurs spécifiées sur lesquelles le producteur s'engage

Classe granulaire	Norme					CODE								
	5.6	11.2	Norme NF P 18-545 Article 10					Gr A						
	d/2	d	D	1.4D	2D	f	FI	AS	C	LA	MBF	S	WA24	
Incertitude U	1	5	5	1	0	0.3	4	0.15	0.003	3	2	0.1	0.5	
V.S.S.+U	6.0	22.0	100.0	100.0	100.0	4.30	24.00	0.350	0.013	28	12.00	0.500	3.0	
V.S.S.	5.0	17.0	99.0	100.0	100.0	4.00	20.00	0.200	0.010	25	10.00	0.400	2.5	
V.S.I.	0.0	2.0	84.0	98.0	100.0	0.00								
V.S.I.-U	0.0	0.0	79.0	97.0	100.0	0.00								
Ecart-type max	1.52	4.55	4.55											

## Partie informative

Résultats de production

	du 06/07/20 au 30/11/20							au 31/07/20					
	2.8	5.6	11.2	16	22.4	f	FI	AS	C	LA	MBF	S	WA24
Maximum	3.2	10.6	98.1	100.0	100.0	1.14	13.10						
Xf+1.25xEcart-types	2.1	7.8	97.5	100.0	100.0	0.99							
Moyenne Xf	1.2	5.9	95.2	100.0	100.0	0.61	10.96	0.023	0.001	14	3.33	0.007	0.6
Xf-1.25xEcart-types	0.2	3.9	92.8	99.9	100.0	0.24							
Minimum	0.3	3.5	91.9	99.7	100.0	0.16	9.29						
Ecart-type	0.73	1.54	1.87	0.06	0.00	0.300	1.318						
Nombre de résultats	24	24	24	24	24	24	6	1	1	1	1	1	1

