

# CODE 011M : Sable 0/4 "Piste TROT" MOUEN

**Producteur :** GKM - Carrières de Mouen

**Petrographie :** Grès feldspathique

**Elaboration :** Tertiaire

## Partie contractuelle

Valeurs spécifiées sur lesquelles le producteur s'engage

**Classe granulaire**

**Norme**

**CODE**

0 4

Norme interne

Sable Hippodrome

	0.063	0.125	0.25	0.5	1	2	4	5	6.3	8	FM	MB	WA24
Incertitude U	1	1	1	4	4	3	3	3	1	0	0.15	0.5	0.5
V.S.S.+U	15.0	23.0	31.0	46.0	64.0	86.0	100.0	100.0	100.0	100.0	4.30	2.50	
V.S.S.	14.0	22.0	30.0	42.0	60.0	83.0	97.0	100.0	100.0	100.0	4.15	2.00	
V.S.I.	6.0	11.0	18.0	30.0	44.0	63.0	82.0	90.0	98.0	100.0	2.40		
V.S.I.-U	5.0	10.0	17.0	26.0	40.0	60.0	79.0	87.0	97.0	100.0	2.25		
Ecart-type max	2.42			4.55	4.85	6.06	4.55	3.03					

## Partie informative

Résultats de production

du 12/02/20 au 03/11/20

	0.063	0.125	0.25	0.5	1	2	4	5	6.3	8	FM	MB	WA24
Maximum	13.1	20.9	29.9	40.5	55.5	80.1	93.2	97.8	100.0	100.0	3.16	1.50	
Xf+1.25xEcart-types	12.2	18.5	27.3	38.6	54.3	79.0	91.2	96.8	100.0	100.0	3.16		
Moyenne Xf	10.9	16.8	25.3	36.5	51.8	75.6	89.2	95.6	99.8	100.0	3.05	1.15	0.3
Xf-1.25xEcart-types	9.6	15.1	23.2	34.4	49.3	72.2	87.2	94.4	99.7	100.0	2.94		
Minimum	9.4	14.9	23.2	34.6	48.7	70.6	87.3	94.5	99.6	100.0	2.86	1.00	
Ecart-type	1.03	1.39	1.62	1.67	2.02	2.72	1.62	0.97	0.12	0.00	0.090	0.184	
Nombre de résultats	15	15	15	15	15	15	15	15	15	15	15	13	1

