

CODE 102E : Gravillon 2/6 ETAVAUX

Producteur : GKM - Carrières d' Etavaux
Petrographie : Grés-Schisteux
Elaboration : Tertiaire

Partie contractuelle

Valeurs spécifiées sur lesquelles le producteur s'engage

Classe granulaire

Norme

CODE

2 6.3

Norme NF P 18-545 Article 10

Gr B

	d/2	d	D		2D		f	FI	AS	C	LA	MBF	S	WA24
	1	2	4.5	6.3	8	12.5								
Incertitude U	1	5	6	5	1	0	0.3	4	0.15	0.003	3	2	0.1	0.5
V.S.S.+U	6.0	20.0	61.0	100.0	100.0	100.0	1.30	39.00	0.350	0.013	28	12.00	0.500	3.0
V.S.S.	5.0	15.0	55.0	95.0	100.0	100.0	1.00	35.00	0.200	0.010	25	10.00	0.400	2.5
V.S.I.	0.0	0.0	25.0	80.0	98.0	100.0	0.00							
V.S.I.-U	0.0	0.0	19.0	75.0	97.0	100.0	0.00							
Ecart-type max		4.55	9.09	4.55										

Partie informative

Résultats de production

	du 16/07/20 au 07/12/20								au 31/07/20						
	1	2	4.5	6.3	8	12.5	f	FI	AS	C	LA	MBF	S	WA24	
Maximum	2.7	6.7	54.9	91.6	99.7	100.0	0.98	25.11							
Xf+1.25xEcart-types	1.5	3.9	44.2	88.9	99.6	100.0	0.63								
Moyenne Xf	0.7	2.0	36.8	85.1	99.1	100.0	0.32	22.05	0.028	0.001	16	3.66	0.019	0.5	
Xf-1.25xEcart-types	0.0	0.0	29.4	81.2	98.6	100.0	0.00								
Minimum	0.0	0.7	29.8	79.9	98.4	100.0	0.08	19.25							
Ecart-type	0.66	1.57	5.95	3.08	0.44	0.00	0.252	1.979							
Nombre de résultats	24	24	24	24	24	24	24	6	1	1	1	1	1	1	

